

Material & Engineering Laboratory-Kaohsiung

Test Report

REPORT NO: KV-07-01724X

OF PAGE NO : 1

: MAR. 16, 2007 DATE

CLIENT

KAO CHEN ENTERPRISE CO., LTD.

PRODUCT DESCRIPTION

Walker

BLACK

STYLE/ITEM NO.

MLE15001(15002,15003,15004) MPE15003(15004,15005,15006)

COLOR

SAMPLE SUBMITTED BY

KAO CHEN ENTERPRISE CO., LTD.

SAMPLE RECEIVED DATE

MAR. 01, 2007

SAMPLE TESTED DATE

MAR. 01, 2007~.MAR. 13, 2007

REMARK

The information mentioned in the above section is provided by testing

applicant(Exclude tested date)

TEST RESULTS:

Test Item	Test Method	Test Result	
		Specimen	Test result
Material Analysis	FTIR(Fourier Transform Infrared Spectrophotometer)	1.Inner material	Main constituent is Polyester
		2.Black foam	Main constituent is EVA
		3. White plastic	Main constituent is Polyethylene
	1.FTIR(Fourier Transform Infrared Spectrophotometer) 2.DSC(Differential Scanning Calorimetry)	4.Base material	Main constituent is Nylon 6
	ASTM E1251-04	5.Metal brace	Main constituent is Aluminum

Note: 1.Brand and Model of FTIR: BIO-RAD FTS-3000

2.Please refer to attached photo for the detail of test part.

The value of required specifications are for reference only. Conformity judgement is the Applicant's final verdict.

SGS Taiwan Ltd.

Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. Any unauthorized alteration forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law. 此報告是遵循本公司言定之通用服務條款所限作發放,請注意此條款列印於背面,亦可在www.sgs.com中查閱。將本公司之義務,免責,管轄構造明確規範之。除非另有說明,此報告結果僅對檢驗之樣品負責。本報告未經本公司書面許可,不可部份複製。對本報告內容或外觀之任何未經授權之變更、僞造、載改皆屬非法,違犯者將會被依法追訴。

TW4475307